

Toughness Verification Test

This is to state that the product indicated was tested according to the procedures shown. Mechanical properties and chemical analysis of the weld deposit were as shown.

Innershield NR-232

431AR

Diameter (in.): 5/64	Current Type & Polarity: DC-	Volts: 20	Shielding Gas: Not Applicable
Code: 4G5LRAD	PHT (°F): 300	WFS (ipm): 125	Flow Rate (cfh): Not Applicable
Position: 3G-UP	INT (°F): 500	Amps: 255	
Thickness (in.): 0.75	Yes Mechanized?	Avg HI (kJ/in): 86.7	
		CTWD (in): 0.75	


This product satisfies the requirements of FEMA 353, Appendix D after exposure for 1 week at 80°F, 80%RH.

Charpy V-notch Test Results	
Temp. (°F)	Energy (ft-lbf)
0	53
	53
	49
70	90
	88
	85

Tensile Test Results				
Aging	UTS (ksi)	YP (ksi)	YS (ksi)	EL (%)
48HRS. @ 220F	78.2	65.8	60.2	30

Chemical Test Results						
C	S	Mn	Si	P	Al	Ni
0.177	0.003	0.65	0.25	0.007	0.53	0.02

State of Ohio, County of Cuyahoga
 Subscribed and sworn to before me this
16th day of January, 2002
Lesiacet
 Notary Public
 My commission expires September 23, 2004



Donald L. Bill
 Donald L. Bill, Certification Supervisor

David A. Fink
 David A. Fink, Manager, Mature Products Consumable R&D

This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of The Lincoln Electric Company affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.