

LNS 4500

CLASSIFICATION

AWS A5.9/A5.9M : ER385
 ISO 14343-A : G 20 25 5 Cu L

GENERAL DESCRIPTION

Fully austenitic stainless steel wire
 To be used for cryogenic application or with non magnetic stainless steels
 Recommended with P2007, P2000 and P7000 fluxes

CHEMICAL COMPOSITION (W%), TYPICAL, WIRE

C	Mn	Si	Cr	Ni	Mo	Cu
0.01	1.8	0.3	20	25.2	4.6	1.5

PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.4
Unit : 25 kg stein basket B450	X

LNS 4500: rev. EN 02