

# Outershield<sup>®</sup> 70

Mild Steel, Flat & Horizontal • AWS E70T-1C-H16, E70T-9C-H16

## Key Features

---

- ▶ High deposition in the flat and horizontal positions
- ▶ Designed for welding with 100% CO<sub>2</sub> shielding gas
- ▶ Excellent bead wetting and low spatter
- ▶ Tolerates mild levels of surface contaminants
- ▶ Stiff wire for easy breaking

## Typical Applications

---

- ▶ Structural fabrication
- ▶ Barge fabrication
- ▶ Heavy fabrication
- ▶ Construction equipment

## Conformances

---

AWS A5.20/A5.20M: 2005	E70T-1C-H16, E70T-9C-H16
ASME SFA-A5.20:	E70T-1C-H16, E70T-9C-H16
ABS:	2YSA
DNV Grade:	II YMS H15
CWB/CSA W48-06:	E492T-9 H16
TUV:	EN 758 T 46 0 R C3 / M3 H10
MIL-E-24403/1:	MIL-70T-1C

## Welding Positions

---

Flat & Horizontal

## Shielding Gas

---

100% CO<sub>2</sub>  
Flow Rate: 40-50 CFH

# Outershield® 70

(AWS E70T-1C-H16, E70T-9C-H16)

## DIAMETERS / PACKAGING

Diameter in (mm)	50 lb (22.7 kg) Coil	600 lb (272 kg) Speed-Feed® Reel	600 lb (272 kg) Speed-Feed® Drum
1/16 (1.6)	ED012782	ED014588	
5/64 (2.0)	ED012785		
3/32 (2.4)	ED012784	ED014120	ED030262

## MECHANICAL PROPERTIES<sup>(1)</sup> – As Required per AWS A5.20/A5.20M: 2005

	Yield Strength <sup>(2)</sup> MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft•lbf)	
				@ -18°C (0°F)	@ -29°C (-20°F)
<b>Requirements</b> AWS E70T-1C-H16 AWS E70T-9C-H16	400 (58) min.	485-655 (70-95)	22 min.	27 (20) min. –	– 27 (20) min.
<b>Typical Results<sup>(3)</sup></b> As-Welded with 100% CO <sub>2</sub>	525-575 (76-83)	620-635 (90-92)	27-28	39-42 (29-31)	31-34 (21-25)
Stress Relieved with 100% CO <sub>2</sub> for 1 hr @ 621°C (1150°F)	525 (76)	555 (80)	27-28	27 (20)	24 (18)

## DEPOSIT COMPOSITION<sup>(1)</sup> – As Required per AWS A5.20/A5.20M: 2005

	%C	%Mn	%Si	%S	%P
<b>Requirements - AWS E70T-1C, E70T-9C</b>	0.12 max.	1.75 max.	0.90 max.	0.03 max.	0.03 max.
<b>Typical Results<sup>(3)</sup></b> As-Welded with 100% CO <sub>2</sub>	0.08	1.41-1.43	0.64-0.73	0.01	0.01

## TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD <sup>(5)</sup> mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
1/16 in (1.6 mm), DC+ 100% CO <sub>2</sub>	25 (1)	3.2 (125)	23-25	170	2.4 (5.3)	2.1 (4.6)	87
		5.1 (200)	25-27	235	3.8 (8.5)	3.4 (7.6)	87
		6.4 (250)	25-28	275	4.8 (10.6)	4.2 (9.2)	87
		7.6 (300)	27-29	310	5.8 (2.7)	5.0 (11.1)	87
		9.5 (375)	29-31	365	7.2 (15.9)	6.4 (14.0)	88
5/64 in (2.0 mm), DC+ 100% CO <sub>2</sub>	28 (1-1/8)	3.2 (125)	23-26	250	3.8 (8.4)	3.2 (7.0)	83
		4.4 (175)	26-28	350	5.4 (11.8)	4.5 (10.0)	85
		5.7 (225)	27-29	375	6.9 (15.2)	5.9 (13.0)	86
		6.4 (250)	29-31	400	7.7 (16.9)	6.5 (14.4)	86
		7.6 (300)	30-32	450	9.2 (20.2)	7.9 (17.4)	86
8.3 (325)	31-33	470	9.9 (21.9)	8.5 (18.8)	86		
3/32 in (2.4 mm), DC+ 100% CO <sub>2</sub>	32 (1-1/4)	3.2 (125)	24-27	335	5.3 (11.7)	4.4 (9.8)	84
		5.1 (200)	28-31	455	8.5 (18.6)	7.3 (16.0)	86
		6.4 (250)	30-32	530	10.6 (23.3)	9.2 (20.2)	87
		7.6 (300)	31-34	590	12.7 (28.0)	11.0 (24.3)	87
		8.3 (325)	33-35	615	13.7 (30.3)	12.0 (26.4)	87

<sup>(1)</sup>Typical all weld metal. <sup>(2)</sup>Measured with 0.2% offset. <sup>(3)</sup>See test results disclaimer below. <sup>(4)</sup>To estimate ESO, subtract 1/4 in (6.0 mm) from CTWD.  
NOTE: This product contains micro-alloying elements. Additional information available upon request.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at [www.lincolnelectric.com](http://www.lincolnelectric.com)

### TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

### CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.