

# Pipelin<sup>®</sup>er 101M

AWS E101T1-GM



Pipelin<sup>®</sup>er 101M is a gas-shielded, flux-cored wire designed for hot, fill and cap pass welding on up to X80 grade pipe. Optimized for automated and semi-automatic pipe welding applications, Pipelin<sup>®</sup>er 101M has a consistent arc and fast freezing slag to maintain a flat bead shape all around the pipe. The electrode is capable of producing Charpy V-Notch impact properties exceeding 27J (20 ft•lbf) @ -40°C (-40°F). For an electrode that meets the demands of automated and semi-automatic pipe welding for X80 grade pipe – choose Pipelin<sup>®</sup>er 101M.

## KEY FEATURES

- ▶ **Consistent Arc** – Designed for optimal performance in automated pipe welding applications where a consistent arc length is critical.
- ▶ **Flat Bead Shape** – Fast freezing slag provides consistent puddle support all the way around the pipe.
- ▶ **Impact Toughness** – Capable of producing weld deposits with impact toughness exceeding 27 J (20 ft•lbf) at -40°C (-40°F).
- ▶ **Q2 Lot<sup>®</sup> Control and Tested** – Certificate showing actual deposit composition and mechanical properties per lot available online.
- ▶ **ProTech<sup>®</sup> Packaging** – Hermetically sealed packaging for moisture resistance.

## WELDING POSITIONS

All

## DIAMETERS / PACKAGING

Diameter mm (in)	10 lb (4.5 kg) Plastic Spool (Vacuum Sealed Foil Bag)	25 lb (11.3 kg) Plastic Spool (Vacuum Sealed Foil Bag)
1.2 (0.047)	ED033807	ED033808

## APPLICATIONS

- ▶ Hot, fill and cap pass welding on up to X80 grade pipe
- ▶ Fully automated pipe welding
- ▶ Semi-automatic pipe welding
- ▶ Meets hardness and chemistry requirements for NACE

## CONFORMANCES

AWS A5.29/A5.29M:	E101T1-GM
ASME SFA-5.29	E101T1-GM
ISO 18276: 2006	ISO 18276-B-T694T1-1MA-N2M2-UH5

## SHIELDING GAS

75-80% Argon/Balance CO<sub>2</sub>  
Flow Rate: 40-60 CFH

**MECHANICAL PROPERTIES<sup>(1)</sup> – As Required per AWS A5.29/A5.29M**

	Yield Strength <sup>(2)</sup> MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft•lbf) @-40°C (-40°F)
<b>Requirements</b> AWS E101T1-GM	610 (88) min.	690-830 (100-120)	16 min.	Not Specified
<b>Typical Performance<sup>(3)</sup></b> As-Welded with 75-80% Argon / Balance CO <sub>2</sub>	660-670 (95-97)	700-720 (101-104)	23-25	61-91 (45-68)

**DEPOSIT COMPOSITION<sup>(1)</sup> – As Required per AWS A5.29/A5.29M**

	%C	%Mn	%Si	%P
<b>Requirements</b> AWS E101T1-GM	Not Specified	0.50 <sup>(4)</sup>	1.00 max.	0.030 max.
<b>Typical Performance<sup>(3)</sup></b> As-Welded with 75% Argon / 25% CO <sub>2</sub>	0.06	1.48-1.61	0.29-0.31	0.008
	%S	%Ni	%Mo	Diffusible Hydrogen (mL/100g weld deposit)
<b>Requirements</b> AWS E101T1-GM	0.030 max.	0.50 <sup>(4)</sup>	0.20 <sup>(4)</sup>	Not Specified
<b>Typical Performance<sup>(3)</sup></b> As-Welded with 75% Argon / 25% CO <sub>2</sub>	0.007	0.76 - 0.84	0.34 - 0.36	4-5

**TYPICAL OPERATING PROCEDURES**

Diameter, Polarity Shielding Gas	CTWD <sup>(5)</sup> mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)
<b>1.2 mm (0.047 in), DC+</b> 75-80% Argon / Balance CO <sub>2</sub>	19 (3/4)	4.4-10.2 (175-400)	23-30	130-275	1.8-4.1 (3.9-9.0)

<sup>(1)</sup> Typical all weld metal. <sup>(2)</sup> Measured with 0.2% offset. <sup>(3)</sup> See test results disclaimer below. <sup>(4)</sup> In order to meet the requirements of the G group, the undiluted weld metal shall have not less than the minimum specified for one or more of the elements listed. <sup>(5)</sup> Strength and elongation properties were obtained from a 0.500 in. tensile specimen artificially aged at 104°C (220°F) for 48 hours as permitted by AWS A5.29:2010.  
NOTE: This product contains micro-alloying elements. Additional information available upon request.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at [www.lincolnelectric.com](http://www.lincolnelectric.com)

**TEST RESULTS**

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

**CUSTOMER ASSISTANCE POLICY**

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.