

ULTRACORE® CLARITY™ M71 LE

Mild Steel, All Positions ▪ AWS E71T-1M-H8, E71T1-M21A0-CS1-H8

KEY FEATURES

- The lowest Manganese Generation Rate (MnGR) of any similarly classified electrode
- Over 80% reduction in MnGR when compared to a standard E71T1-1M flux-cored electrode
- Assists efforts to reduce exposure to Mn
- Designed for welding with 75% Argon / 25% CO₂ shielding gas
- H8 diffusible hydrogen levels
- ProTech® foil bag packaging

WELDING POSITIONS

All

CONFORMANCES

AWS A5.20/A5.20M: E71T-1M-H8
AWS A5.36/A5.36M: E71T1-M21A0-CS1-H8
CWB/CSA W48-06: E491T-9M-H8*

**1/16 diameter only, others pending*

TYPICAL APPLICATIONS

- General Fabrication

SHIELDING GAS

75% Argon / 25% CO₂
 Flow rate: 40-50 CFH

DIAMETERS / PACKAGING

Diameter in (mm)	33 lb (14.9kg) Fiber Spool
0.045 (1.1)	ED036253
1/16 (1.6)	ED036252

MECHANICAL PROPERTIES⁽¹⁾

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation (%)	Charpy V-Notch J (ft·lbf) @-18°C (0°F)
Requirements				
AWS A5.20: E71T-1M-H8	400 (58) min	480-655 (70-95)	22 min	27 (20) min
AWS A5.36: E71T1-M21A0-CS1-H8	400 (58) min	480-655 (70-95)	22 min	27 (20) min
Typical Results⁽³⁾				
As-Welded with 75% Ar/25% CO ₂	430-440 (62-64)	525-540 (76-78)	25-26	38-85 (28-63)

⁽¹⁾ Typical all weld metal. ⁽²⁾ Measured with 0.2% offset. ⁽³⁾ See test results disclaimer

DEPOSIT COMPOSITION⁽¹⁾

	%C	%Mn	%Si	%S
Requirements				
AWS A5.20: E71T-1M-H8	0.12 max	1.75 max	0.90 max	0.03 max
AWS A5.36: E71T1-M21A0-CS1-H8				0.030 max
Typical Results⁽³⁾				
As-Welded with 75% Ar/25% CO ₂	0.08-0.09	0.12-0.14	0.49-0.54	0.006-0.007
	%P	%Ni	Diffusible Hydrogen (ml/100g weld deposit)	
Requirements				
AWS A5.20: E71T-1M-H8	0.03 max	0.50 max	8.0 max	
AWS A5.36: E71T1-M21A0-CS1-H8	0.030 max		8 max	
Typical Results⁽³⁾				
As-Welded with 75% Ar/25% CO ₂	0.010	0.44-0.46	4-6	

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD ⁽⁴⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage (Volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
0.045 in (1.1 mm), DC+ 75% Ar/25% CO ₂	19 - 25 (3/4 - 1)	5.1 (200)	20-24	165	2.1 (4.6)	1.8 (4.0)	84-88
		6.4 (250)	21-25	180	2.6 (5.8)	2.3 (5.1)	
		7.6 (300)	22-26	215	3.1 (6.9)	2.8 (6.1)	
		8.9 (350)	23-26	235	3.7 (8.1)	3.3 (7.2)	
		10.2 (400)	24-29	260	4.2 (9.3)	3.7 (8.2)	
		11.4 (450)	25-30	280	4.8 (10.6)	4.3 (9.4)	
		12.7 (500)	26-31	300	5.1 (11.2)	4.8 (10.5)	
1/16 in (1.6 mm), DC+ 75% Ar/25% CO ₂	19 - 25 (3/4 - 1)	3.2 (125)	22-25	170	2.2 (4.9)	2.0 (4.5)	83-90
		3.8 (150)	22-25	185	2.9 (6.3)	2.5 (5.6)	
		5.1 (200)	23-26	230	3.8 (8.4)	3.3 (7.3)	
		6.4 (250)	24-27	260	4.7 (10.4)	4.2 (9.2)	
		7.6 (300)	25-29	295	6.8 (14.9)	5.1 (11.3)	
		10.2 (400)	27-31	325	7.6 (16.7)	6.8 (14.9)	
		12.7 (500)	29-33	460	9.5 (21.0)	8.6 (19.0)	

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer ⁽⁴⁾To estimate ESO, subtract 1/4 in (6.0 mm) from CTWD.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.