

METALSHIELD® MC®-80Ni1 BUY AMERICA



Low Alloy ▪ AWS E80C-Ni1

KEY FEATURES

- H4 diffusible hydrogen levels
- Low spatter and excellent arc stability
- Deoxidizing agents minimize pre- and post-weld clean up
- Enhanced silicon island management
- Low temperature impact properties – Capable of exceeding 40 J (29 ft•lbf) @ -45°C (-50°F)
- Excellent bead shape and profile
- Meets the AWS E80C-Ni1 H4 requirement for tensile and yield strength in both the as-welded condition and after 2 hrs of post-weld heat treating (PWHT)
- Made in the U.S.A. using steel melted and manufactured in the U.S.A.
- Meets the Buy America requirements of the American Recovery and Reinvestment Act (ARRA)

WELDING POSITIONS

All

CONFORMANCES

AWS A5.28, ASME SFA-5.28: E80C-Ni1-H4
AWS A5.36, ASME SFA-5.36: E80T15-M13A5-Ni1-H4,
 E80T15-M12A5-Ni1-H4,
 E80T15-M21A5-Ni1-H4

TYPICAL APPLICATIONS

- Robotics/Hard automation
- Weathering grades of the appropriate strength ASTM A588 & A709 steels
- Structural fabrication
- Heavy fabrication

SHIELDING GAS

75-95% Argon / Balance CO₂
 95-99% Argon / Balance O₂
 Flow Rate: 40-60 CFH

DIAMETERS / PACKAGING

Diameter in (mm)	33 lb (15 kg) Plastic Spool (Vacuum Sealed Foil Bag)
0.045 (1.1)	ED036363
0.052 (1.3)	ED036364
1/16 (1.6)	ED036365

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.28/A5.36

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft•lbf) @ -45°C (-50°F)
Requirements – AWS A5.28: E80C-Ni1-H4 AWS A5.36: E80T15-M13A5-Ni1-H4	470 (68) min	550 (80) 550-690 (80-100)	24 min 19 min	27 (20) min
Test Results⁽³⁾ As-Welded with 98% Argon / 2% O ₂	530-620 (77-90)	605-660 (88-96)	24-28	60-100 (43-76)
As-Welded with 92% Argon / 8% CO ₂ Stress Relieved 2 hrs. @ 621°C (1150°F)	510 - 570 (74 - 83) 540 (78)	585 - 635 (85 - 92) 620 (90)	27 - 29 29	85 - 120 (61 - 89) 85 (61)
As-Welded with 75% Argon / 25% CO ₂ Stress Relieved 2 hrs. @ 621°C (1150°F)	480 - 540 (70 - 78) 470 (68)	565 - 615 (82 - 89) 565 (82)	28 - 31 29	40 - 95 (29 - 70) 80 (58)

⁽¹⁾ Typical all weld metal. ⁽²⁾ Measured with 0.2% offset. ⁽³⁾ See test results disclaimer

DEPOSIT COMPOSITION⁽¹⁾ – As Required per AWS A5.28/A5.36

	%C	%Mn	%Si	%S	%P	%Cu
Requirements – AWS A5.28: E80C-Ni1-H4 AWS A5.36: E80T15-M13A5-Ni1-H4	0.12 max	1.50 max 1.75 max	0.90 max 0.80 max	0.025 max 0.030 max	0.030 max	0.35 max Not Specified
Test Results⁽³⁾						
As-Welded with 98% Argon / 2% O ₂	0.07 - 0.08	1.31 - 1.35	0.48 - 0.50	0.024 max	0.012	0.03 - 0.05
As-Welded with 92% Argon / 8% CO ₂	0.05 - 0.07	1.22 - 1.30	0.43 - 0.47	0.024 max	0.012	0.03 - 0.05
As-Welded with 75% Argon / 25% CO ₂	0.05 - 0.06	1.14 - 1.19	0.38 - 0.42	0.024 max	0.012	0.04 - 0.06
	%Ni	%Cr	%Mo	%V	Diffusible Hydrogen (mL/100g weld deposit)	
Requirements – AWS A5.28: E80C-Ni1-H4 AWS A5.36: E80T15-M13A5-Ni1-H4	0.80 - 1.10 1.25 - 2.60	Not Specified 0.15 max	0.30 max	0.03 max	4.0 max 4 max	
Test Results⁽³⁾						
As-Welded with 98% Argon / 2% O ₂	0.84 - 0.86	0.05 max	0.10 max	0.01 max	3 - 4	
As-Welded with 92% Argon / 8% CO ₂	0.83 - 0.86	0.05 max	0.10 max	0.01 max	3 - 4	
As-Welded with 75% Argon / 25% CO ₂	0.80 - 0.85	0.05 max	0.10 max	0.01 max	3 - 4	

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD ⁽⁵⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage ⁽⁶⁾ (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
0.045 in. (1.1 mm), DC+ 92% Argon / 8% CO ₂	19-25 (3/4-1)	5.1 (200)	21-23	180	2.5 (5.5)	2.2 (4.9)	89
		6.4 (250)	22-25	220	3.1 (6.8)	2.9 (6.3)	93
		7.6 (300)	22-26	250	3.7 (8.2)	3.4 (7.4)	90
		8.9 (350)	22-27	280	4.4 (9.6)	3.9 (8.9)	92
		10.2 (400)	23-27	310	4.9 (10.9)	4.5 (10.3)	94
		12.7 (500)	23-28	350	6.2 (13.6)	5.6 (13.0)	96
		15.2 (600)	25-29	380	7.4 (16.3)	6.9 (15.6)	96
0.052 in. (1.3 mm), DC+ 92% Argon / 8% CO ₂	25-32 (1-1 1/4)	3.8 (150)	22-25	200	2.4 (5.3)	2.2 (4.8)	91
		5.1 (200)	23-26	250	3.2 (7.0)	3.0 (6.6)	94
		6.4 (250)	24-28	290	4.0 (8.8)	3.8 (8.4)	95
		7.6 (300)	26-29	320	4.8 (10.5)	4.7 (10.4)	99
		10.2 (400)	27-30	360	6.4 (14.0)	6.4 (14.0)	99
1/16 in. (1.6 mm), DC+ 92% Argon / 8% CO ₂	25-32 (1-1 1/4)	3.8 (150)	22-25	235	3.4 (7.5)	3.0 (6.7)	89
		5.1 (200)	23-26	295	4.4 (9.7)	4.2 (9.2)	95
		6.4 (250)	24-28	350	5.8 (12.7)	5.4 (11.8)	93
		7.6 (300)	26-29	395	6.9 (15.2)	6.5 (14.3)	94
		10.2 (400)	27-30	465	9.2 (20.2)	8.8 (19.3)	96

⁽¹⁾ Typical all weld metal. ⁽²⁾ Measured with 0.2% offset. ⁽³⁾ See test results disclaimer. ⁽⁴⁾ To estimate ESO, subtract 1/4 in. (6.0 mm) from CTWD.

⁽⁵⁾ For shielding gas blends of 95-99% Argon / Balance O₂, decrease voltage by 1-2 volts.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.

