

Blue Max[®] Orbital TIG 308/308L N

Stainless Steel • AWS ER308, ER308L

Key Features

- ▶ Ultra clean wire
- ▶ Q2 Lot[®] - Certificate showing actual wire composition and calculated ferrite number (FN) available online
- ▶ Batch Managed Inventory
- ▶ "N" Designate - design modified to meet special chemistry requirements
- ▶ 0.05% max Cobalt
- ▶ Prior to using this material for ASME Boiler and Pressure Vessel Code Section III applications, please contact the Lincoln Electric Specials Department to receive a Certified Material Test Report (CMTR) which meets all requirements of NCA-3860

Typical Applications

- ▶ Nuclear Energy
- ▶ Thermal Energy
- ▶ Petroleum Processing
- ▶ Pressure Vessel
- ▶ Contractors
- ▶ Process Piping

Conformances

AWS A5.9/A5.9M: 2006 ER308, ER308L
 ASME SFA-A5.9: ER308, ER308L

Welding Positions

All

Shielding Gas

100% Argon

DIAMETERS / PACKAGING

Diameter in (mm)	2 lb (0.9 kg) Spool 8 lb (3.6 kg) Carton	10 lb (4.5 kg) Spool
0.035 (0.9)	ED034141	ED034143

Blue Max® Orbital TIG 308/308L N

(AWS ER308; ER308L)

DEPOSIT COMPOSITION⁽¹⁾ – As Required per AWS A5.9/A5.9M: 2006

	%C	%Mn	%Si	%S	%P	%Cr
Requirements						
AWS ER308L	0.03 max.	1.0 - 2.5	0.30 - 0.65	0.03 max.	0.03 max.	19.5 - 22.0
Test Results⁽²⁾	0.02	1.20	0.39	<0.01	0.02	20.20
	%Ni	%Mo	%Cu	%N	%N	FN
Requirements						
AWS ER308L	9.0 - 11.0	0.75 max.	0.75 max	Not Specified	0.05 max.	Not Required
Test Results⁽²⁾	10.30	0.16	0.11	0.02	0.04	Not Required

⁽¹⁾ Typical all weld metal. ⁽²⁾ See test results disclaimer below.

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.